

PROPERLA®

EXTERIOR FACADE COATING

ProPERLA Exterior Facade Coating is a highly advanced two-coat coloured coating product for use on a range of substrates that require a coloured exterior wall coating.



Key Features:

- Super Hydrophobic - in conformance with DIN 4108
- Water-soluble
- Breathable
- Self-Cleaning
- Extends the life-span of all mineral building surfaces
- Prevents discoloration
- Low film tension
- Prevents salt efflorescence
- Prevents growth of moss, algae and lichens
- Choice of classic colours available

Recommended for: For use on mineral substrates that require a coloured exterior wall coating, as well as renovation finishes on stable silicate and matt dispersion paint coatings, synthetic resin plasters and intact thermal insulation composite systems. Keeps facades dry to maximum depth permanently.

Binder type

Silicon resin emulsion, and special silan polymer

Density: Approx. 1.50

Gloss: Flat

Colour: see colour card

Tinting colours: Pastel colours

Packaging: Pot 10 Litres

Spraying data: Airless

Nozzle size: 0.021 inch

Spray angle: 50°

Spray pressure: 150-200 bars

Thinner addition: up to 10% water

Cleaning of tools: Immediately after use with water.

Application utilities: Brush, roller, spray gun

Storage: Cool, however above freezing. Seal opened containers well.

Consumption: Approx. 150ml/m² per coat on smooth surfaces. Correspondingly more on rough surfaces. Determine exact consumption quantities by testing.

Minimum temperature for application and drying: + 5° C (air and subsurface)

Application of coatings: The previous coat must be completely dry before the next coat is applied on the facade. Drying time increases accordingly in cool or moist weather.

Surface preparation: see reverse side

Primer coat: see reverse side

Filling work (if applicable): Use a suitable Filler according to the processing guidelines.

First Coat: proPERLA diluted up to 10% with water.

Second Coat: proPERLA diluted up to 10% with water.

Notes: Do not use proPERLA® products with coating materials of other types such as silicate or dispersion paints or dispersion or silicate based full colour paints. Do not mix it with tinting concentrates.

Do not mix proPERLA® with other coating systems. Resilient facade coatings with highly thermoplastic properties are not a suitable subsurface. They must be removed, e.g. by leaching. See EU Safety Data Sheet for detailed product information relevant for safety.